



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C09D 9/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/20518</b> <b>(43) International Publication Date:</b> 13 April 2000 (13.04.00)
<b>(21) International Application Number:</b> PCT/US99/21764 <b>(22) International Filing Date:</b> 22 September 1999 (22.09.99) <b>(30) Priority Data:</b> 09/164,748 1 October 1998 (01.10.98) US <b>(71) Applicant:</b> S.C. JOHNSON COMMERCIAL MARKETS, INC. [US/US]; 8310 16th Street, M/S 510, Sturtevant, WI 53177 (US). <b>(72) Inventors:</b> HERNANDEZ, Paul, M.; 504 Leith Avenue, Waukegan, IL 60085 (US). BROWN, Lance, D.; Apartment 201, 2750 - 87th Street, Sturtevant, WI 53177 (US).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> CONCENTRATED STRIPPER COMPOSITION AND METHOD		
<b>(57) Abstract</b>  The present invention is directed to a composition for stripping coatings from a surface, the composition including: a. A solvent mixture composed of a phenyl substituted alkyl alcohol and an alkyl or aryl glycol ether or an alkyl or aromatic alcohol; b. A coupler composed of a salt formed from a water soluble organic amine and an acid comprising at least one C7-C18 ethoxylated anionic surfactant; c. Optionally water. The use of the C7-C18 ethoxylated anionic surfactant provides a stripper which can be diluted in water of various compositions yet provides an effective stripping/cleaning agent.		

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## CONCENTRATED STRIPPER COMPOSITION AND METHOD

CROSS-REFERENCE TO RELATED APPLICATIONS: None

5

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH  
OR DEVELOPMENT: None

## BACKGROUND OF THE INVENTION

10

## Technical Field

This invention relates to compositions and methods of using compositions to strip or remove coatings such as typical floor finishes and cleaning of such surfaces. More particularly, it relates to a stripping composition which can be diluted and still provide efficient stripping.

15

## Background Art

There are available numerous concentrated stripper and cleaner/degreaser formulations for use in conjunction with floors. U.S. Patent 5,637,559 from 3M discloses a floor stripping composition which includes a phenyl substituted alkyl alcohol which preferably is benzyl alcohol having a water solubility of at least 0.1 weight percent, a coupler consisting of a fatty acid of C8 in chain length and water. The coupler is at least 3.0 times the amount necessary to completely solubilize the phenyl substituted alkyl alcohol in the water. Preferred couplers are the salt of a monofunctional water-soluble amine and an organic acid comprising at least one water-insoluble organic acid having from 6-10 carbon atoms. U.S. Patents 5,080,831; 5,080,822 and 5,158,710 from Buckeye International, Inc. teach the use of sparingly water soluble solvents when used with a hydrotrope to form a aqueous solution or microemulsion that can used as a stripper. The solvents, such as benzyl alcohol, cited in these patents have a water solubility ranging from 0.2 to approximately 6 weight percent in water. In the '831 Patent the solubilizing agent is present in an amount not exceeding approximately twofold that required to completely solubilize the organic solvent. Japanese Patent JP

20  
25  
30

9689885 assigned to S.C. Johnson Inc. teaches the use of a phenyl substituted alkyl alcohol having a water solubility of at least 0.1 weight percent. Benzyl alcohol is also disclosed with Tall Oil Fatty Acid as the organic acid which when combined with a monofunctional water-soluble amine as the coupler form an aqueous floor finish stripper.

- 5           Other cleaning compositions with a specific solvent or surface active agent are described in U.S. Patents 4,749,509 and 5,543,073.

### SUMMARY OF THE INVENTION

- Contrary to the teachings of the art, the inventors have discovered that
- 10   compositions containing at least two specific solvents from the select class of slightly water-soluble organic solvents and a specific coupler, wherein the coupler is present at greater than 2.0 times that required to completely solubilize the solvent are much more efficient in removing a variety of floor finishes at higher dilutions than prior art compositions. The other unique property of the inventive composition is the ability to
- 15   remove these floor finishes of higher dilutions than the prior art compositions and the ability to remain stable in the concentrate as well as in dilution. Another surprising attribute that has been uncovered is the ability of these compositions to be diluted in hard water and still being stable and effaceous. The use of a new coupling agent has also given these compositions the ability to be prepared using alkaline salts such as NaOH and
- 20   KOH and still be stable in the concentrate as well as in dilution which the prior art compositions are not. The use of a new coupler has also the added feature of being less viscous and therefore is easier to be diluted via dispensing equipment and other typical dilution methods.

The objects of the invention therefore are:

- 25           a.     Providing an improved floor coating stripper composition.
- b.     Providing an improved stripper composition of the foregoing kind which is compatible with water of various compositions.
- c.     Providing an improved stripper composition of the foregoing kind which can be diluted in the 1:30-1:50 range and still be effective.
- 30           d.     Providing an improved stripper of the foregoing kind which can be dispensed with automated dispensing systems.

The foregoing objects are accomplished and the shortcomings of the prior art are accomplished by the compositions of this invention which are suitable for stripping of various floor finish coatings, such as acrylic, urethane and epoxy polymer base, from a variety of surfaces, such as vinyl composition, terrazzo, marble, linoleum, concrete and the like as well as an effective cleaner/degreaser after being diluted with water from 1 part of said compositions to 50 parts of water and still remove the finish. In one embodiment, the compositions may be formulated comprising:

- a. About 1-55% by weight of a solvent mixture composed of a phenyl substituted alkyl alcohol and about an equal amount of an alkyl or aryl glycol ether or an alkyl or aromatic alcohol, the solvent mixture effective in removing at least 20% of a standard acrylic floor sealer/finish from a composition vinyl tile in fewer than 2.5 minutes;
- b. a coupler composed of a salt formed from a water soluble organic amine and an acid comprising at least one C7-C18 ethoxylated anionic surfactant, the coupler and the solvent mixture present in a weight ratio of about 1:1.2 to about 1:2.0 wherein the amount of the coupler is at least 2.0 times the amount necessary to completely solubilize the solvent mixture; and
- c. optionally water.

In another embodiment, the water-soluble organic amine is monoethanolamine or a combination of monoethanolamine and potassium hydroxide.

In yet another embodiment, the acid is a C9-C11 ethoxylated anionic surfactant and has 4 moles of ethoxylation.

In still another embodiment, the phenyl substituted alkyl alcohol is benzyl alcohol, and the alkyl glycol ether is ethylene glycol monohexyl ether.

In yet another embodiment, the coupler includes tall oil.

"Diluted with water" as used herein means the inventive compositions are reduced in actives concentration by adding from 0.1 part of 100 parts of water per part of inventive composition. Specific dilution ratio are dependent on the end use, as shown in the following Examples. Additionally the water hardness described is from 0 ppm to 450 ppm hardness as  $\text{CaCO}_3$ .

"Effective amount" when referring to the solvent blend of phenyl substituted alkyl alcohol and alkyl glycol ether means that is present in an amount which removes at least 20 percent of a standard urethane/acrylic floor finish from a composition vinyl tile within fewer than 2.5 minutes, in accordance with a standard test (see Test Methods section).

5 As used herein the term "coupler" refers to a compound or a physical or chemical combination of compounds having the capability of increasing the phase-stability of the compositions of the invention. The couplers that are preferred comprise low molecular weight (molecular weights in the 300 to 800 range) organic monoethanolamine and alkaline salts either sodium hydroxide or potassium hydroxide with organic acid (tall oil) and ethoxylated carboxylic acid (C9-C11 carboxylic acid with 4 moles of ethoxylation; trade name of Neodox 1-4).

The compositions can also include an effective amount of chelating agents (e.g. ethylene diaminetriacetic acid) and other surfactants for added stability and enhanced hard water stability but are not crucial to this invention. Water soluble solvents such as ethylene glycol monobutyl ether can also be used with this invention to enhance cleaning and stripping ability.

The compositions of the invention are substantially more effective in removing multiple/difficult to remove floor sealer/finishes comprising of urethane/acrylic polymers than the previously described patented compositions, as shown in the Examples.

20 Another aspect of the invention is a method of removing a sealer/finish coating from a surface, the method comprising:

- a. applying to the coating a composition within the invention; and
  - b. allowing the composition to contact the coating for a time sufficient to at least partially remove the coating. As used herein
- 25 "coating" is meant to include a single layer or multiple layers of the same composition and coatings comprising two or more layers, each layer comprising of dissimilar compositions.

Preferred methods comprise of abrading the coating after a predetermined contact time between the coating and the composition, such as with an open three dimensional non-woven pad which is attached to a conventional floor maintenance machine.

Alternatively, the composition may be applied and removed using other natural and synthetic fiber-based cloth.

Further aspects and advantages of the invention will become apparent from the description of the preferred embodiments which follows.

## DESCRIPTION OF PREFERRED EMBODIMENTS

5

The compositions of the present invention are especially useful in stripping a variety of difficult to strip "sealer/finishes" from flooring materials such as composition vinyl tiles, linoleum, marble, terrazzo, concrete and the like. The compositions of the invention may also be employed in degreasing grease, oil, cooking oils and the like from a variety of floors in restaurants, homes, automobile shops and the like. The compositions of the invention may also be employed in cleaning a variety of other surfaces other than floors. The various ingredients are discussed in more detail.

### Phenyl Substituted Alkyl Alcohols

Phenyl substituted alkyl alcohols are the first solvents and function as the coating dissolver and/or grease solubilizing component of the compositions of the invention. The phenyl substituted alkyl alcohols are from the class of "sparingly" or "slightly" water soluble organic solvents which have water solubility of at least 0.1 weight percent, more preferable ranging from about 0.2 to about 6 weight percent. Phenyl substituted alkyl alcohols useful in the invention include benzyl alcohol, alpha-phenylethyl alcohol, betaphenylethyl alcohol, ethylene glycol phenyl ether, and the like. One of the preferred phenyl substituted alkyl alcohols which is slightly water-soluble is benzyl alcohol.

The second solvent used in the invention is from the alkyl glycol ether family and it functions in that it increases the wetting as well as the dissolving ability of the benzyl alcohol. The preferred secondary solvent is ethylene glycol hexyl ether (Trade name Hexyl Cellosolve) and it too is a "sparing soluble" solvent with similar properties of low toxicity, availability, relative nonhazardous to transport with a essentially a non-odor as benzyl alcohol.

The term "alkyl" as used herein means an alkyl group having 1-10 carbon atoms.

In addition to the water solubility criteria mentioned previously, it is also desirable but not essential that the phenyl substituted alkyl alcohols and the alkyl glycol ether employed in the invention have a relatively low volatility or high flash point (in

excess of 60 C.) exhibit a low level of odor, be chemically stable, non-toxic, nonhazardous and commercially available.

We have found the use of phenyl substituted alkyl alcohol in conjunction with the use of alkyl or aryl glycol ether or an alkyl or aromatic alcohol in equal proportions in the composition as having unexpected results not found by the use of either one individually. This solvent mix is in an amount sufficient to remove the coating to which it is applied, the amount varying with the coating or residue to be removed. Further compositions within the invention preferably have the following weight ratios of active ingredients:

- Phenyl substituted alkyl alcohol to coupler, from 1:1 to 1:2.0. Preferably 1:1.6.
- Alkyl glycol ether to coupler, from 1:1 to 1:2.0. Preferably 1:16.
- Phenyl substituted alkyl alcohol to anionic surfactant from 1:10. Preferably 1:1.5.
- Alkyl glycol ether to anionic surfactant from 1:10. Preferably 1:5.5.

For particularly hard to remove coatings the weight percentage of phenyl substituted alkyl alcohols/alkyl glycol ethers in the ready-to-use composition may be as high as 10 weight percent. For easier to strip finishes or cleaning, one may dilute the concentrates so that the weight percentage of phenyl substituted alkyl alcohols/alkyl glycol ethers is as low as 0.5 weight percent. A preferred ready-to-use composition includes from 1.0 to 3.5 wt % of solvent. These concentrations of solvent combinations may be diluted as the concentrates listed in Table 1. For cleaning compositions the solvent mixture will have the power to remove greasy residues at less than 1 weight percent.

The following Table 1 illustrates two of the preferred compositions of this invention.

Table 1

		<u>Concentrate 1</u>	<u>Concentrate 2</u>
<u>Ingredient</u>			
30	Benzyl alcohol	27.5	27.5
	Hexyl Cellosolve	27.5	27.5
	Monoethanolamine	35.0	17.0
	Tall Oil Fatty acid	5.0	
	Neodox 1-4	5.0	10.0
35	Potassium hydroxide	--	18.0



### Couplers

Couplers function to increase the phase stability of the composition by increasing the apparent water solubility of the solvent mix. Suitable couplers for use in the compositions of the present invention include the salt of a low molecular weight  
5 monofunctional amine as well as alkaline salts such as sodium hydroxide and potassium hydroxide as well as organic acid. These couplers allow the use of high concentration of solvent coupled/emulsified and are instrumental in the stability of the product as well as stability of the diluted product. Particularly preferred monofunctional amines include water soluble organic amines such as monoethanolamine (MEA), 2-aminomethylpropanol  
10 (AMPS), and other n-alkyl substituted derivatives of these.

Preferred acids include fatty acids (tall oil) as well as C7-C18 carboxylic acids with ethoxylation of 1-10 moles of ethylene oxide. For this invention tall oil and the carboxylate Neodox 1-4 available from Shell Chemical Co. is especially preferred. We have also found that by the inclusion of the ethoxylated organic acid that that it not only  
15 improves product stability but enhances the stability of the concentrate when diluted in hard water so that no additional builder or chelate is necessary. Another key attribute found with the unique use of alkaline salts like sodium hydroxide and potassium hydroxide. We have also found that by the use of these carboxylic acids combinations we obtained less viscous compositions which are much easier dispensed from venturi  
20 type dispenser than prior art compositions.

The couplers are present in ready-to-use compositions of the invention such that the amount of the coupler is always less than or equal to the solvent blend used. This a departure from previous taught patents where said coupler are either equal to or as much as 3.0 times necessary to solubilize the solvents in water.

25 Other optional surfactants that can be used in this invention are nonionics, in particular the Tergitols, such as Tergitol 15-S-9, which has been found to be useful in making formulations not containing ethoxylated carboxylates, however they are not the preferred surfactants. Tergitol is a trademark of Union Carbide Corporation for C8-C18 nonionic surfactants with 1-15 moles of ethylene oxide. Other anionic surfactants that  
30 have found utility are the well known hydrotropes like sodium xylene sulfonate as well as the following: dodecylbenzene sulfonic acid, sodium dodecylbenzene sulfonate, potassium dodecylbenzene sulfonate, triethanolamine dodecylbenzene sulfonate,

morpholinium dodecylbenzene sulfonate, ammonium dodecylbenzene sulfonate, isopropylamine dodecylbenzene sulfonate, sodium tridecylbenzene sulfonate, sodium dinonylbenzene sulfonate, potassium didodecylbenzene sulfonate, dodecyl diphenyloxide disulfonic acid, sodium dodecyl diphenyloxide disulfonate, isopropylamine decyl

5 diphenyloxide disulfonate, sodium hexadecyloxypoly (ethyleneoxy) (10) ethyl sulfonate, potassium octylphenoxypoly (ethyleneoxy) (9) ethyl sulfonate, sodium alpha C<sub>12-14</sub> olefin sulfonate, sodium hexadecane-1 sulfonate, sodium ethyl oleate sulfonate, potassium octadecenylsuccinate, sodium oleate, potassium laurate, triethanolamine myristate, morpholinium tallate, potassium tallate, sodium lauryl sulfate, diethanolamine lauryl

10 sulfate, sodium laureth (3) sulfate, ammonium laureth (2) sulfate, sodium nonylphenoxypoly (ethyleneoxy) (4) sulfate, sodium diisobutylsulfosuccinate, disodium laurylsulfosuccinate, tetrasodium N-laurylsulfosuccinimate, sodium mono decyloxypoly (ethyleneoxy) (4) phosphate, sodium di decyloxypoly (ethyleneoxy) (6) phosphate, and potassium mono/di-octylphenoxypoly (ethyleneoxy) (9) phosphate. These surfactants

15 and hydrotropes were found to be especially useful in formulating other compositions that contained water soluble solvents like butyl Cellosolve.

These compositions can also be thickened and used for various other applications especially for vertical surfaces and as an aerosol applications. Prior art describes the use of specific ingredients that are useful for those applications.

20 In the methods of the invention, the compositions of the invention may be applied with a mop, poured onto the surface to be cleaned or stripped as well as dispensed from a suitable dispenser such as one of the venture type (J-Fill dispenser). The compositions may also be applied by conventional floor maintenance machines, or they may be sprayed as an aerosol or non-aerosol upon the surface to be cleaned. Spraying can be

25 accomplished by conventional mechanical spraying devices or by using an aerosol dispensing container with a sufficient amount of suitable aerosol propellant, for example, low boiling alkanes or mixtures thereof, such as a mixture of isobutane and propane..

Further application of the compositions and methods of the invention will be understood with reference to the following Examples wherein all parts and percentages

30 are by weight unless otherwise specified. These Examples are set forth to illustrate the invention and are not intended to limit the invention in any way.

### EXAMPLES

The concentrated compositions shown in Table 1 above were diluted with water at the dilutions indicated in Table 2 to formulate the compositions of Examples 1-2.

Table 2 also shows additional formulations and the various key compositions tested to arrive at the compositions of this invention. The compositions of comparative Examples A-C in Table 3 were formulated in accordance with the teaching of U.S. Patent No. 5,158,710; U.S. Patent No. 5,637,559 and Japanese Patent 9689885 and are provided in prior art Examples A-C.

The composition of Examples 1-7 and Comparative Examples A-C were tested to determine their proficiency in removing 10 coats of a commercially available acrylic finishes from a composition vinyl tile strip, the finish available from SC Johnson Professional, Racine, WI under the trade designation of Signature. To clean previously stripped tiles 10 coats of finish was applied. After each coat a crayon marker was used to identify each coat. The Signature coated tiles were burnished (high speed burnisher) after 3, 6 and 10th coat prior to oven aging in order to enhance and duplicate actual aged coatings found in commerce. After all 10 coats were applied the tiles were aged in a oven at 125 F for 100 hours to allow the coating to fully harden and thus simulate aged coating.

The compositions of Examples 1-7 as well as Comparative Examples A-C were then tested via the use of a Gardner Scrubber by placing strips of tiles treated and identified onto the bed of the Scrubber. Each strip of tile was stripped with a red non-woven nylon pad which was attached to a pulley and is dragged over the tile to simulate the type of abrasion done in actual practice. To each strip of tile 15 mls of diluted concentrated stripper solutions were applied to the tile. Immediately after the solution was applied the Gardner Scrubber was started and number of coats removed versus cycles was recorded. In all Examples, the number of maximum cycles used was 100 cycles or less depending on complete removal.

As a second method to determine stability of both the concentrate as well as dilution, comparative as well as compositions were tested via two methods. The first method for composition stability was to make up the composition and subject it to both 40 F and 125 F in a refrigerator or oven for at least 3 days. The results are also included. A second test which determined the stability of the diluted product was done by diluting

the concentrates in synthetic 300 ppm hard water (as CaCO<sub>3</sub>). The results from this test is also indicated in the Tables. These tests are used by those skilled in the art of developing compositions and are readily accepted as an indication of the overall micro-emulsion properties and efficiency of the surfactants/solvents used.

- 5 The third test run was viscosity at 44 F which gives a good indication of the rheology of the composition and is crucial in dispensing from venturi type dispenser (J-Fill), The lower the viscosity the more accurate the dilutions which are critical in performance. Viscosities greater than 50 cps can be used but viscosities less than 40 cps are preferred.

10

Table 2

	<u>Ingredient</u>	<u>Ex. 1</u>	<u>Ex. 2</u>	<u>Ex. 3</u>	<u>Ex. 4</u>	<u>Ex. 5</u>	<u>Ex. 6</u>	<u>Ex. 7</u>
	Monoethanol Amine	35	17	35.0	35	35	35	35
15	Benzyl Alcohol	27.5	27.5	27.5	13.75	41.25		
	Hexyl Cellosolve	27.5	27.5	27.5	41.25	13.75	27.5	27.5
	1-Butoxy Propanol						27.5	
	Ethylene Glycol Phenyl Ether							27.5
	Tall Oil Fatty Acid	5.0		5.0	10.0	10.0	5.0	5.0
20	Tergitol 15-S-9			5.0				
	Neodox 1-4	5.0	10.0					
	Neodox 45-6						5.0	5.0
	Potassium Hydroxide		18.0					
25	No. of coats Signature Removed							
	Dilution @ 1:15	9	10	8				
	@ 1:25	8	8	6				
	Dilution Stability-Conc.	pass*	pass	pass	sep*	sep	sep	sep
	@1:15(hard water)	pass	pass	pass	sep	sep		
30	@1:25(hard water)	pass	pass	pass				
	@1:256(hard water)	pass	pass	pass				
	Viscosity @44 F(cps)	44.8	76.8	44.8				

Pass-refers to solution/emulsion is stable for 24 hours

- 35 Sep. refers to separation or precipitation after dilution

PRIOR ART EXAMPLESExample A - 3M Formulation

5	<u>Ingredient</u>	<u>%/Wt</u>
	Monoethanolamine	33.9
	Benzyl Alcohol	39.9
	n-Octanoic Acid	25.0
	FC-135	0.20
10	Dye	0.50
	Chelating Agent	0.50

Example B - Butchers Full Impact

15	<u>Ingredient</u>	<u>%/Wt</u>
	Monoethanolamine	23.2
	Benzyl Alcohol	47.9
	Dipropylene Glycol n-Butyl Ether	13.5 (water soluble solvent)
	Tall Oil FA Salt (Amine)	15.4

20

Example C - Japan Power - Go

	<u>Ingredient</u>	<u>%/Wt</u>
	Monoethanolamine	18.0
25	N-(,B Aminoethyl) Ethanolamine	15.0
	Benzyl Alcohol	35.0
	Tall Oil Fatty Acid	5.0
	Fluoroalcohol Phosphate and Eto	0.1
	Quatermonium Salt	
30	Perfluoro Alky Phosphate (15%)	0.6
	Fluorinated Acrylic Ester	
	Copolymer (20%)	<u>0.1</u>
	Water	26.2

35

Table 3Comparative Examples A-C

5	3M Formulation	A		
	Butchers Full Impact		B	
	Japan Power-Go			C
	No. of coats Signature Removed			
10	Dilution @1:15	7	8	7
	@1:25	6	7	3
	Dilution Stability -Conc	pass	pass	pass
	@1:15(hard water)	pcpt	pcpt	pcpt
	@1:25(hard water)	pcpt	pcpt	pcpt
	@1:256(hard water)	pcpt	pcpt	pcpt
15	Viscosity @ 44F(cps)	102.4	25.6	27.0

Pcpt-refers to substantial precipitation when concentrate is diluted.

These Examples A-C as well as Examples 1-7 illustrate the importance of the ethoxylated anionic surfactant coupler if it is to be diluted and still act as an effective stripper.

While certain alkyl and aryl ethers as well as alkyl alcohols have been indicated for use with the phenyl substituted alkyl alcohols of this invention, other alkyl and aryl ethers as well as alkyl and aromatic alcohols can be employed which are described as follows according to their water solubility.

**WATER SOLUBLE:** >6.0 Wt. Percent soluble in water

	Ethylene Glycol Monobutyl Ether	Triethylene Glycol n-Butyl Ether
	Propylene Glycol methyl ether	Diethylene Glycol Methyl Ether
30	2-Tertiary Butoxy Ethanol	Triethylene Glycol Methyl Ether
	Dipropylene Glycol Methyl Ether	Ethylene Glycol Monopropyl Ether
	Tripropylene Glycol Methyl Ether	Diethylene Glycol Monomethyl Ether
	Propylene Glycol n-Propyl Ether	Methoxytriglycol
	Dipropylene Glycol n-Propyl Ether	Ethoxytriglycol
35	Diethylene Glycol n-Butyl Ether	
	Butoxytriglycol	

**SPARINGLY WATER SOLUBLE:** <6.0 Wt. Percent soluble in water

1-phenoxy-2-propanol	Cyclohexanol
Propylene Glycol n-Butyl Ether	iso-octanol
Dipropylene Glycol n-Butyl Ether	Texanol (Eastman)
5 Tripropylene Glycol n-Butyl Ether	n-decanol
Propylene Glycol Phenyl Ether	Diethylene Glycol mono hexyl Ether
2-Octanol	2-Ethyl Hexanol

10

**INDUSTRIAL APPLICABILITY**

The compositions of this invention are useful in stripping and removing coatings such as floor finishes as well as the cleaning of such surfaces. They can be diluted with water and still provide stripping and cleaning properties.

What is claimed is:

1. A composition suitable for stripping coatings from a surface the composition comprising:

- 5                   a. 1-55% by weight of a solvent mixture composed of a phenyl substituted alkyl alcohol and about an equal amount by weight of an alkyl or aryl glycol ether or an alkyl or aromatic alcohol, said solvent mixture effective in removing at least 20 % of a standard acrylic floor sealer/finish from a composition vinyl tile in fewer than 2.5 minutes;
- 10                   b. a coupler composed of a salt formed from a water soluble organic amine and an acid comprising at least one C7-C18 ethoxylated anionic surfactant, said coupler and said solvent mixture present in weight ratio of solvent mixture present in a weight ratio of 1:1.2 to 1:2.0 wherein the amount of the coupler is at least 2 times the amount necessary to completely solubilize the solvent mixture;
- 15                   and
- c. optionally water.
2. Composition in accordance with Claim 1 wherein the water-soluble organic amine is monoethanolamine or a combination of monoethanolamine and
- 20                   potassium hydroxide.
3. Composition in accordance with Claim 1 wherein the acid is a C9-C11 ethoxylated anionic surfactant.
- 25                   4. Composition in accordance with Claim 2 wherein the acid has 4 moles of ethoxylation.
5. Composition in accordance with Claim 1 wherein the phenyl substituted alkyl alcohol is benzyl alcohol.
- 30                   6. Composition in accordance with Claim 1 wherein the alkyl glycol ether is ethylene glycol monohexyl ether.



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/21764

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D9/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 637 559 A (KORELTZ FRANCIS J ET AL) 10 June 1997 (1997-06-10) cited in the application the whole document ----	1-9
A	WO 97 32937 A (JOHNSON COMPANY LTD ;SADO MITSUO (JP)) 12 September 1997 (1997-09-12) the whole document ----	1-9
A	US 5 080 822 A (VANEENAM DONALD N) 14 January 1992 (1992-01-14) cited in the application ----	
A	US 5 411 678 A (SIM JOHNNY O) 2 May 1995 (1995-05-02) column 2, line 44-66 column 3, line 26-57; examples 5-13 -----	1,9

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

1 February 2000

Date of mailing of the international search report

08/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5318 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Miller, A

7. The Composition in accordance with Claim 1 wherein the coupler further includes tall oil.
8. Composition in accordance with Claim 1 wherein the solvent mixture has  
5 a water solubility of at least 0.1 weight percent.
9. A method of removing a coating from a surface comprising:  
applying to the coating the composition of Claim 1; and  
allowing the composition to contact the coating for a time sufficient to at  
10 least partially remove the coating.

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 99/21764

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5637559 A	10-06-1997	BR 9405912 A	30-01-1996
		CA 2159611 A	13-10-1994
		DE 69412080 D	03-09-1998
		DE 69412080 T	08-04-1999
		EP 0692004 A	17-01-1996
		ES 2120608 T	01-11-1998
		JP 8508523 T	10-09-1996
		WO 9422965 A	13-10-1994
WO 9732937 A	12-09-1997	JP 9241687 A	16-09-1997
		AU 712709 B	11-11-1999
		AU 2230397 A	22-09-1997
		BR 9707875 A	27-07-1999
		CA 2247107 A	12-09-1997
		EP 0885267 A	23-12-1998
US 5080822 A	14-01-1992	AU 7694991 A	30-10-1991
		CA 2080352 A,C	11-10-1991
		EP 0525032 A	03-02-1993
		JP 2528053 B	28-08-1996
		WO 9115565 A	17-10-1991
US 5411678 A	02-05-1995	US 5487789 A	30-01-1996